FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15/ **Date: 18-03-2015**

TEST REPORT ON WET MIX MACADAM MIX
(GRADATION TEST)

Sub: To conduct Gradation test on Wet Mix Macadam (WMM) Mix.
{Project*: Improvements to Roads and Drains at Defence Colony Sahakaranagara 20th Cross Road 9th Main, B Block and 21st B Cross Road 2nd Main C Block in Ward No.08 of Kodigehalli Sub-Division}

Ref.: Letter No. Testing/BUB/2014-15, dated 16-03-2015

Sample supplied to lab by: Sri.R.Madhusudhan, Contractor, Bangalore.

Report required for: Assistant Executive Engineer, Kodigehalli Sub-Division. BBMP, Bangalore.

TEST RESULTS

1. Gradation Test:

TABLE 1.1

Sieve Size mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Specified Limits as per MoRTH Specifications, IV Revision-2001
53.00	**100.00**	100
45.00	**96.00**	95-100
26.50	**---**	-
22.40	**71.30**	60-80
11.20	**43.00**	40-60
4.75	**33.00**	25-40
2.36	**24.10**	15-30
0.600	**18.60**	8-22
0.075	**4.90**	0-8

AE-B

*As Furnished by Client

The Results relate only to the items tested

The test Reports are Accepted

18/3/2015

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Verified

Dr. MANJESH L
ME (Civil Engg.) Ph.D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e-mail: manjeshl@yahoo.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Date: 18-03-2015

TABLE 12 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2007)
1	Flakiness & Elongation Index	01	**22.70%**	Not more than 30 %
2	Impact Value	----,,----	**23.60 %**	Not more then 24.00 % for BC Not more then 27.00 % for DBM Not more then 30.00 % for BM/WMM

*As Furnished by Client

The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING * BANGALORE UNIVERSITY

18/03/2015

Dr. MANJESH .L
ME(Civil Engg.) Ph.D. MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus,
BANGALORE 560 056.
E-mail maniesnl@yahoo.com

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15/

Date: 25-03-2015

TEST REPORT ON BITUMINOUS MIXES
(BITUMEN EXTRACTION TEST & GRADATION TEST)

Sub: Testing of Bitumen Premix Sample (Semi Dense Bituminous Concrete-SDBC).
{Project*: Improvements to Roads and Drains at Defence Colony Sahakaranagara 20th Cross Road 9th Main, B Block and 21st B Cross Road 2nd Main C Block in Ward No.08 of Kodigehalli Sub-Division}

Ref.: Letter No. Testing/BUB/2014-15, dated 23-03-2015

Sample supplied to lab by: Sri.R.Madhusudhan, Contractor, Bangalore.

Report required for: Assistant Executive Engineer, Kodigehalli Sub-Division. BBMP, Bangalore.

TEST RESULTS:

1. The bitumen content obtained after subjecting the sample for Bitumen Extraction test = **5.03%**
2. **Gradation Test** :

Sieve Size, mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Gradation requirement as per Table 500-15 of MORTH Specifications-2001 (Grading – 2)
13.2	**100**	100
9.5	**98.00**	90—100
4.75	**45.10**	35—51
2.36	**34.20**	24—39
1.18	**24.10**	15—30
0.3	**18.00**	09—19
0.075	**4.20**	03—08

AE-B

* As furnished by Client.
The Results relate only to the items tested.

The test Reports are Accepted

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Verified

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail: manjeshl@yahoo.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Date: 25-03-2015

TABLE 12 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2007)
1	Flakiness & Elongation Index	01	**24.20%**	Not more than 30 %
2	Impact Value	----,,----	**25.30 %**	Not more then 24.00 % for BC Not more then 27.00 % for DBM Not more then 30.00 % for BM/WMM
3	Water absorption	----,,----	**0.50%**	Not more than 1.0 %
4	Stripping test. (Coating and stripping of Bitumen aggregate mixtures)	----,,----	**97.20 %**	Minimum retained coating 95.0 %

*As Furnished by Client

The Results relate only to the items tested.

DEPARTMENT OF CIVIL ENGINEERING * BANGALORE UNIVERSITY *

25/03/2015

Dr. MANJESH .L
ME(Civil Engg.) Ph.D.. MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University. Jnanabharathi Campus,
BANGALORE 560 056.
E-mail: maniesnl@yahoo.com